

## AHA1283

### Texture additive for powder coatings

#### Description

**AHA1283** is a fluorocarbon polymer wax which can be used as a special textured additive in powder coatings applicable in housing electric equipment such as VCD and audio/video, office appliance, playground equipment and other many industrial applications, especially computer.

#### Specification

Appearance	Off-white very fine powder
Melting ranges (°C)	100-140

#### Characteristics

- Applicable to any powder coating systems such as pure epoxy, hybrid, polyester/TGIC or **Primid** and **PU** etc to provide a special fine-grained texture finish.
- Very attractive and consistent texture finish compared with other existing texture additives.
- Unnecessary or greatly decrease of flow modifier and benzoin in powder formulation, therefore the coating cost may be further reduced.

#### Use levels

Approx. 0.5-2% by weight, calculated on total formulation.

#### Incorporation

AHA1283 is added to the binder/pigment blend before extrusion.

#### Storage

- Store in temperature between 2 and 35°C or cool dry place to avoid caking. Keep package closed after using. Keep away from fire.
- Based on our experience the shelf life of this product is at least 3 years.

#### Package

Packing with PE lined paper plate-drum. Net weight 25 Kg per drum.

Version II-11-2023

#### Notice:

The key technical data or specifications for the above product described in this paper may be changed from time to time due to improvement constantly. **AHA** reserves the right to change the specifications of its products without prior notice.

Although the information in this paper is based on our own investigation and is believed reliable, **AHA** can not assume any responsibility for performance or results obtained through the use of our products herein described. Neither we nor our agents shall be liable for any injury, loss or damages directly or indirectly caused by our products. The user is held to check the quality, safety and all other properties of our product before using. Nothing herein is to be taken as permission or recommendation to practice any patented invention without a license.