


Technical Data Sheet

AHA 6810

TGIC

Description

AHA6810 is triglycidyl isocyanurate, chemical structure:






Triglycidyl isocyanurate

CAS No: 2451-62-9

EINECS: 219-514-3

Typical property

Appearance	[visual]	Form A Irregular Granule, White Color by crushed granulation process	
		Form B Regular pills, White Color (Diameter 5 mm) by melting granulation process	
		Form C Regular Noodle Form, White Color by extrusion granulation process	
Melting point (°C)		95-125	
EEW (g/eq.)		110 (max.)	
EPI residue		≤150 mg/kg	

Notice:

The key technical data or specifications for the above product described in this paper may be changed from time to time due to improvement constantly. **AHA** reserves the right to change the specifications of its products without prior notice.

Although the information in this paper is based on our own investigation and is believed reliable, **AHA** can not assume any responsibility for performance or results obtained through the use of our products herein described. Neither we nor our agents shall be liable for any injury, loss or damages directly or indirectly caused by our products. The user is held to check the quality, safety and all other properties of our product before using. Nothing herein is to be taken as permission or recommendation to practice any patented invention without a license.

Chlorine content (%)	≤0.6
Volatiles (%)	≤0.5

Herein described to be typical properties and do not constitute specification limits.

Application

AHA6810 is mainly used as hardener used in formulating exterior durable polyester powder coatings.

Regulatory status

AHA6810 complies with TSCA (USA), DSL/NDSL (Canada) and IECSC(China).

Storage

Store in temperature between 2 and 30°C or cool dry place to avoid caking. Keep package closed after using. Keep away from fire.

Based on our experience the shelf life of this product is at least 1 years.

Package

Packaging with PE bag. Net weight 25Kg per bag.

Version IIII - 03-2024

Notice:

*The key technical data or specifications for the above product described in this paper may be changed from time to time due to improvement constantly. **AHA** reserves the right to change the specifications of its products without prior notice.*

Although the information in this paper is based on our own investigation and is believed reliable, **AHA** can not assume any responsibility for performance or results obtained through the use of our products herein described. Neither we nor our agents shall be liable for any injury, loss or damages directly or indirectly caused by our products. The user is held to check the quality, safety and all other properties of our product before using. Nothing herein is to be taken as permission or recommendation to practice any patented invention without a license.